





Sistema DAPc<sup>®</sup> Declaración Ambiental de Productor de Construcción

		NAL FEATURES N ISO 10545-2	
Length	2700 MM		
Thickness	6 MM		
Width	1200 MM		
Length and width deviation	Below 0.15%		+/-0.3%*
Side straightness deviation	Below 0.15%		+/-0.3%*
Squareness deviation	Below 0.15%		+/-0.3%*
Surface flatness deviation	Below 0.15%		+/-0.4%*
*ISO-13006:2015 UNE-EN 14411:2017			

	MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11
Breaking strenght	>1100 N
Modulus of rupture	> 45 N/MM2
Abrasion resistance	<140 MM3
*ISO-13006:2015 UNE-EN 14411:2017	

	HYGIENIC FEATURES UNE-EN ISO 10545-13-14	
Chemical resistance	MIN B	
Stain resistance	5	
Resistance to thermal shock	CUMPLE	
Flammability	A1	
*ISO-13006:2015 UNE-EN 14411:2017		

	ANTI-SLIP VALUE CEN/TS 41901/02, DIN-51130 y ASTM A137.1			
Dynamic coefficient of friction	<0.42			
Slip resistance (pendulum-wet)	CLO			
Pendulum test value (ptv)	DRY>36-LOW_WET<25-HIGH			
Slip resistance (pendulum-dry)	>40			
*ISO-13006:2015 UNE-EN 14411:2017			 	

	PACKING
Sales units per box	3.240441 M2/BOX
Sales units per pallet	71.289695 M2/PAL
Sales units per unit	3.240441 M2/PIECE



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

# PORCELANOSA Grupo

## ADDITIONAL NOTES

Avoid direct access from the outside if no abrasive protection device is provided.

### SCOPE OF USE

Technical code-1 Technical code-2 1 - Coating 0 - No additional requirements

#### **RECOMMENDED USE LOCATIONS**

#### Various

Cladding of bonded or mixed facades

Facade cladding with mechanical anchors



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.