

Model: DECO SAVANNAH CALIZA 59,6X150(A) Codes: 100330300 Water absorption: BIII - Revestimiento (10%<=E<=20%) Finish: Glazed / Standard Tone variations: V2 Rectified: Yes



DIMENSIONAL FEATURES UNE-EN ISO 10545-2				
Thickness	12.5 mm	+/-5%*		
Width	596 mm			
Length	1500 mm			
Length and width deviation	Below 0.15%	+/-0.3%*		
Side straightness deviation	Below 0.15%	+/-0.3%*		
Squareness deviation	Below 0.15%	+/-0.3%*		
Surface flatness deviation	Below 0.15%	+/-0.4%*		
*ISO-13006:2018 UNE-EN 14411:2016				

FEATURES

Natural-looking, non-glossy surface finish.

General deshaded design with a degree of color and appearance variation. Finish with clearly defined protrusions that give the surface a feeling of volume.

Name given to the finish of those tiles dimensionally improved after the firing process.

Wall installation

MECHANICAL FEATURES UNE-EN ISO 10545-4-6-7-11				
Breaking strength	>600 N	>600N*		
Modulus of rupture	>15 N/mm2	>=12N/mm2*		
Crazing resistance	Resists 3 cycles			
*ISO-13006:2018 UNE-EN 14411:2016				
HYGIENIC FEATURES				

UNE-EN ISO 10545-13-14:1995				
Chemical resistance	Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases	B Min.*		
Stain resistance *ISO-13006:2018 UNE-EN 14411:2016	Class 5. Easy cleaning with water	3 Min.*		

	PACKING	
Sales units per box	2.681924 M2/BOX	
Sales units per pallet	48.274629 M2/PAL	
Sales units per unit	0.893975 M2/PIECE	



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.

100330300 DECO SAVANNAH CALIZA



SCOPE OF USE

Technical code-1

1 - Use on walls



Do not use cleaning agents containing hydrofluoric acid. It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint. For big sizes, it is recomended to fix with mortars containing polymeric additives and to use the double glueing technique. Mosaic tiles must be grouted. This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.