## L'ANTIC COLONIAL

Model: AC4 HOME 1L KAPRUN

Codes: 100297715 Group: G-200

Format: 19,3X138,3X0,8CM



COMPOSITION					
		Size	Material	Type of material	
	Layer 1	0.2	Melamine	Aminoplastic thermosetting resins	
	Layer 2	0.2	Decorative paper		
	Layer 3	7.5	HDF	High density fibre board	
	Layer 4	0.1	Backside	Sheets of kraft paper impregnated with phenolic resins	

## **FEATURES**



Imitates the surface of wood



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Is suitable for installing on water radiant heating



PanEuropean Forest Certification that guarantees to consumers the origin of the products from sustainably managed forests



23. Intensive residential



Abrasion-resistance level as per Standard UNE-EN 13329



Beveled cut on all 4 edges of the board for emphasizing size



20 year warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Format where only one board has been used to finish the entire base surface



Environmental Product Declarations for Construction (DAPcons®) are an essential instrument for environmental improvement in the construction sector and, therefore, a useful tool for technicians, manufacturers and users. DAPcons® certifications cover products from the different stages of a building. They provide objective, agreed and verified information on a product.



Safety and joint durability are the main features of this easy installation system that guarantees the elimination of gaps between boards throughout the floor's lifetime. The pressure exerted between boards reinforces the union and prevents it from being carried out incorrectly.



32. General commercial





1/2

It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.

AC4 HOME 11 KAPRUN

## L'ANTIC COLONIAL

DIMENSIONAL FEATURES						
Item thickness	≤0.50 mm	EN 13329*				
Length of face	0.50 mm	EN 13329*				
Width of face	∆medio≤0.10 medio/máx-min≤0.20 mm	EN 13329*				
Squareness of the item (q)	≤0.20 mm	EN 13329*				
Straightness of face	≤0.3 mm/M	EN 13329*				
Flatness of item (f)	fw cóncavo≤0.15/fw convexo≤0.20/fl cóncavo≤0.50/fl convexo≤1.00 %	EN 13329*				
Joint between items	medio≤0.15/máx≤0.20 mm	EN 13329*				
Difference in height among items	max≤0.15 prom≤0.10 mm	EN 13329*				
Dimensional variations related to changes in relative moisture	≤0.9 mm	EN 13329*				
Uv light fastness	mejor nivel 4 escala de grises/mejor nivel 6 cianoescala	EN 20105-A02 / EN ISO 105-B02*				
Surface stripping	≥1.25 N/mm2	EN 13329*				

LABORATORY TESTS						
Resistance to abrasion	AC4	UNE EN 13329:2000*				
Impact resistance	(bola pequeña) (bola grande)≥12 N/≥750 MM	EN 13329*				
Resistance to staining	Grado 5 (G 1 y 2) y Grado 4 (G 3)	EN 438-2.15*				
Resistance to cigarette burns	4	EN 438-2.18*				
Swelling in thickness	≤18%	EN 13329*				
Moisture upon leaving factory	4 - 7 %					
Dimensional stability	≤0.90 mm	EN 13329*				
Formaldehyde emissions	<0.1 ppm (E1)	EN 717-1*				
Slip resistance (wet pendulum) irhd 55	CL 1 (35)	EN 16165 Anexo C*				
Tensile strength of joints	≥1 kN/m	ISO 24334*				
Fire resistance	Cfl-s1	EN 13501*				
Heat resistance	0.0780 M2*K/W	ISO 8302*				
Thermal conductivity	0.1026 W/M*K					
Acoustic insulation	IIC 61/STC 53	ASTM E492-09 / ASTM E90-09*				
Dynamic coefficient of friction (dcof)	0.64	ANSI A137.1*				
Density of the board	850 ±7% kg/m3-6.8 kg/m2	UNE EN 323*				
Slip resistance (pendulum-dry)	CL 3 (55)	EN 16165 Anexo C*				

	PACKING
Sales units per box	2.402256 M2/BOX
Sales units per pallet	124.917293 M2/PAL
Sales units per unit	0.266917 M2/PIECE
Sale unit	M2
Base unit	ST
Sales units per square meter	1 M2
Net weight	7.253183 KG/M2
Gross weight	7.429268 KG/M2

SPECIAL PIECES									
SAP	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net Weight	Gross weight
100297697	IGUALACION HOME 1L KAPRUN 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.7 KG/PIECES	0.72 KG/PIECES
100297726	MAMPERLAN HOME 1L KAPRUN 7X120X3	G-163	2 PIECES/BOX	200 PIECES/PAL	11.9 PIECES/M2	-	-	1.58 KG/PIECES	1.64 KG/PIECES
100297761	TRANSICION HOME 1L KAPRUN 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.7 KG/PIECES	0.72 KG/PIECES
100297764	ZOCALO HOME 1L KAPRUN 8X225X1,4	G-107	12 PIECES/BOX	648 PIECES/PAL	5.56 PIECES/M2	-	-	1.57 KG/PIECES	1.62 KG/PIECES





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.

28/08/2025