## L'ANTIC COLONIAL

Model: AC4 RESIDENCE 1L IDAHO

Codes: 100201389 Group: G-200

Format: 19,3X138X0,8CM





COMPOSITION						
		Size	Material	Type of material		
	Layer 1	0.2	Melamine	Aminoplastic thermosetting resins		
	Layer 2	0.2	Decorative paper			
	Layer 3	7.5	HDF	High-density Fiber Board and water-repellent glues		
	Layer 4	0.1	Backside	Sheets of kraft paper impregnated with phenolic resins		

## **FEATURES**



Imitates the surface of wood





 $20\,\text{year}$  warranty for domestic use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Format where only one board has been used to finish the entire base surface



Environmental Product Declarations for Construction (DAPcons®) are an essential instrument for environmental improvement in the construction sector and, therefore, a useful tool for technicians, manufacturers and users. DAPcons® certifications cover products from the different stages of a building. They provide objective, agreed and verified information on a product.



23. Intensive residential



Abrasion-resistance level as per Standard UNE-EN 13329



Beveled cut on all 4 edges of the board for emphasizing size



Installation system where gluing the boards to the floor is not necessary. They are placed on a foam, joined together, as long as the product does not already have a foil on the back of the piece.



5 year warranty for commercial use valid for laminate floors that have been installed in rooms where they are exposed to normal wear and tear for their recommended End Use Category in accordance with EN 13329.



Is suitable for installing on water radiant heating



It is one of the easiest to install and safest systems in the market. We just need to adjust the board to be installed longitudinally to the one already placed, by applying a soft pressure without the need for any type of tool. Both pieces will fit and will be secured thanks to the safety abo. It is just as simple to take apart, which makes for a quick disassembly



32. General commercial





1/2

It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.

## AC4 RESIDENCE 11 IDAHO

## L'ANTIC COLONIAL

	DIMENSIONAL FEATURES	
Item thickness	≤0.50 mm	EN 13329*
Length of face	0.50 mm	EN 13329*
Width of face	∆medio≤0.10 medio/máx-min≤0.20 mm	EN 13329*
Squareness of the item (q)	≤0.20 mm	EN 13329*
Straightness of face	≤0.30 mm/M	EN 13329*
Flatness of item (f)	fw cóncavo≤0.15/fw convexo≤0.20/fl cóncavo≤0.50/fl convexo≤1.00 %	EN 13329*
Joint between items	medio≤0.15/máx≤0.20 mm	EN 13329*
Difference in height among items	Max≤0.15/Prom≤0.10 mm	EN 13329*
Dimensional variations related to changes in relative moisture	≤0.90 mm	EN 13329*
Uv light fastness	escala azul: no inferior categoría 6-Escala gris: No inferior a categoría 4	EN 438-2,16*
Surface stripping	≥1.25 N/mm2	EN 13329*

LABORATORY TESTS						
Resistance to abrasion	AC4	UNE EN 13329:2000*				
Impact resistance	(Bola grande) (Bola pequeña) 750 mm/≥35 mm	UNE EN 13329*				
Resistance to staining	Grado 5 (G 1 y 2) y Grado 4 (G 3)	EN 438*				
Resistance to cigarette burns	4	EN 438*				
Swelling in thickness	<18%	EN 13329*				
Moisture upon leaving factory	4 -10 %					
Formaldehyde emissions	E1	EN 717-1*				
Slip resistance (wet pendulum) irhd 55	CL 2 (39)	EN 16165 Anexo C*				
Tensile strength of joints	≥1kN/m MPA	EN 13329*				
Fire resistance	Cfl-s1	EN 13501*				
Heat resistance	0.065 M2*K/W	EN 12667*				
Thermal conductivity	0.13 W/M*K	EN 12667*				
Dynamic coefficient of friction (dcof)	0.65	ANSI A137.1*				
Density of the board	850 kg/m3-6.8kg/m2	UNE EN 323*				
Slip resistance (pendulum-dry)	CL 3 (50)	EN 16165 Anexo C*				

	PACKING
Sales units per box	2.13072 M2/BOX
Sales units per pallet	119.32032 M2/PAL
Sales units per unit	0.26634 M2/PIECE
Sale unit	M2
Base unit	ST
Sales units per square meter	1 M2
Net weight	7.31396 KG/M2
Gross weight	7.497935 KG/M2

SPECIAL PIECES									
SAP	Description	Group	Boxes	Pallet	Units	SKU	Basic Unit	Net Weight	Gross weight
100202651	IGUALACION RESIDENCE IDAHO 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.68 KG/PIECES	0.7 KG/PIECES
100202638	MAMPERLAN AC4 RESIDENCE 1L IDAHO 7X120X3	G-163	2 PIECES/BOX	200 PIECES/PAL	11.9 PIECES/M2	-	-	1.58 KG/PIECES	1.64 KG/PIECES
100202655	TRANSICION RESIDENCE IDAHO 4X270X1	G-155	20 PIECES/BOX	1000 PIECES/PAL	9.26 PIECES/M2	-	-	0.7 KG/PIECES	0.72 KG/PIECES
100202662	ZOCALO RESIDENCE IDAHO 8X220X1,5	G-107	14 PIECES/BOX	560 PIECES/PAL	5.68 PIECES/M2	-	-	1.8 KG/PIECES	1.86 KG/PIECES





It is advisable to follow the installation and maintenance instructions published by L'ANTIC COLONIAL, S.A., observing in any case the legal or regulatory requirements that may exist for each area of use. Do not use aggressive cleaning agents, such as acids, or metallic or sharp elements. In public places, this material must comply with the slipperiness requirements of the Spanish Technical Building Code. This document is purely commercial and may not be used in any legal or administrative proceedings, neither as an expert opinion nor as documentary evidence, unless expressly authorized by L'ANTIC COLONIAL, S.A.

28/08/2025