



## HARD MAPLE TORONTO

The golden straw hues found in this 3-strip, North American maple floor from the American Naturals Collection are specially selected to create a subtle and harmonious expression. The silk lacquer finish gives the floor a polished appearance and brings out the natural character of the timber. The even finish protects the wood from daily wear, without adding artificial shine.

PRODUCT DETAILS		FACTS		TECHNICAL PROPERTIES		
Article Number	153N15AP50KW240	Design	3-strip	Moisture	EN13183	7%±2%
EAN Code	7393969018838	Grading	Calm	content		
Surface treatment	Silk lacquer	Range	Kährs Original	Minimun Mean Density kg/m³ >500 kg/m³		
Dimensions	2423 x 200 x 15 mm	Collection	American Naturals	Reaction To Fire	EN13501-1	Dfl-s1
Weight per Package (kg)	23 kg	Formaldeh	Formaldehyde	EN717-1	E1	
Area per Package (m²)	2.9 m <sup>2</sup>	Resandable	2-3 times	Emission		
Area per pallet (m²)	0 m <sup>2</sup>	Natural/Stained	Natural	Content PCP	CEN/TR14823	≤ 5 x 10-6n
Package info	Packages may contain start and stop boards.	Brinell Value	4,8	Breaking Strength N/mm <sup>2</sup>	EN1533	NPD
		Joint	Woodloc® 5S			
		Floor heating	No			
DETAIL DESCRIPTION		Warranty	30 years	<ul><li>Thermal Conductivity</li></ul>	EN12664	0,14 W/mK
Even colour with minor variations. Small sized knots in limited numbers allowed.		Wear-layer material	Hardwood	Thermal Resistance R-Value		.11 (m2K/W)
		Core material	Pine/Spruce lamella	Biological	EN350-2	Class 1
COLOUR CHANGE		Thickness (mm)	15 mm	Durability		
Changes from cream white to golden cream.		Installation method	Floating, Glue-down	CARB2		Compliant

## Other products in this collection











Walnut Georgia

Walnut Montreal

Walnut Hartford

Hard Maple Toronto



Cherry Savannah

## CERTIFICATES



















## **Descriptions & Imagery**

All samples, images and product description, plus photo and brochure specifications are there for the sole purpose of giving an approximate idea of the items described in them. They shall not form part of the contract or have any contractual force and should be viewed for illustrative purposes only. We cannot guarantee that your computer's display or the quality of the print will accurately reflect the colour of the products. Your product may vary slightly from the images within this literature.