

Model: SADDLE TOPO 45X120(A)

Codes: 100363985

Tone variations: V2

Rectified: Yes



## DIMENSIONAL FEATURES

UNE-EN ISO 10545-2

|                             |             |          |
|-----------------------------|-------------|----------|
| Thickness                   | 10 mm       | +/-5%*   |
| Width                       | 450 mm      |          |
| Length                      | 1200 mm     |          |
| Length and width deviation  | Below 0.15% | +/-0.3%* |
| Side straightness deviation | Below 0.15% | +/-0.3%* |
| Squareness deviation        | Below 0.15% | +/-0.3%* |
| Surface flatness deviation  | Below 0.15% | +/-0.4%* |

\*ISO-13006:2018 UNE-EN 14411:2016

## FEATURES

General deshaded design with a degree of color and appearance variation.

Name given to the finish of those tiles dimensionally improved after the firing process.

## MECHANICAL FEATURES

UNE-EN ISO 10545-4-6-7-11

Crazing resistance Resists 3 cycles

\*ISO-13006:2018 UNE-EN 14411:2016

## HYGIENIC FEATURES

UNE-EN ISO 10545-13-14:1995

|                     |  |         |
|---------------------|--|---------|
| Chemical resistance | Class "A" for swimming pools and cleaning products (resists attack). Minimum Class "B" for acids and bases | B Min.* |
| Stain resistance    | Class 5. Easy cleaning with water  | 3 Min.* |

\*ISO-13006:2018 UNE-EN 14411:2016

## PACKING

|                        |                   |  |
|------------------------|-------------------|--|
| Sales units per box    | 1.619958 M2/BOX   |  |
| Sales units per pallet | 64.798315 M2/PAL  |  |
| Sales units per unit   | 0.539986 M2/PIECE |  |

## RECOMMENDED USE LOCATIONS

### Various

Cladding of bonded or mixed facades

Facade cladding with mechanical anchors

### System Certification



Do not use cleaning agents containing hydrofluoric acid.

It is recommended to fix tiles with a minimum joint of 1,5 mm. Do not fix without joint.

For big sizes, it is recommended to fix with mortars containing polymeric additives and to use the double gluing technique.

Mosaic tiles must be grouted.

This document is only commercial and cannot be used as expert opinion, documentary evidence or in any legal or administrative procedure unless authorized by PORCELANOSA S.A.